

# Monitoring the electrical properties and modified insulation of enhancing XLPE high voltage cables

Abirami T  
Research Scholar  
Dept. of EEE  
Sona College of  
Technology(Autonomous)  
Salem,TamilNadu  
India

DR.Karthik B  
Associate Professor  
Dept. of EEE  
Sona College of  
Technology(Autonomous)  
Salem,TamilNadu  
India

DR.N.P.Subramaniam  
Assistant Professor  
Dept. of EEE  
Pondicherry EngineeringCollege  
Puducherry,TamilNadu  
India

**Abstract**— Electrical treeing is the dominating failure phenomena in solid insulating material. Treeing occurs due to voids, dust and impurities present in the insulation material, change in the crystalline structure, stress occurring in the semi-crystalline structure and environmental factors. The growth characteristics of electrical tree is analyzed by injecting high voltage continuously using transformer in XLPE sample

particles are controlled and it can be probable to manage solar inclusion in both solar PV (photovoltaic) and solar thermal purposes. At present, the core nanoparticle was established a zero backward scattering with improved onward scattering on Si (Silicon) substrate while plasmon of surface can be placed in solar cell's front.

**Keywords**—XLPE, high voltage,treeing,nano particles

## I. INTRODUCTION

The solid high-voltage cable insulation's treeing can be a frequent breakdown method and electrical faults are occurred in underground high voltage cables. Treeing occurs due to voids, dust and impurities present in the insulation material, change in the crystalline structure, stress occurring in the semi-crystalline structure and environmental factors. In this work, the inception and propagation of the tree is monitored at regular interval of time. The length of the tree, the partial discharge and leakage current at the time of propagation of the tree is also monitored.

## II. EVERY DAY WITH METALS

### A. Different other forms of metals

In everyday life, the pure fundamental silver can be the exceptional electrical conductor meet. Steel, Copper, aluminum, brass and gold can be acted. The electricity is conducted by a few metals better than any recognized material at room temperature having low temperatures. This kind of occurrence can be known as superconductivity, and a material that can behave that method can be known as a superconductor.

### B. The surface ligands or the nano particles

In general, the interfacial layer can be an essential element of nanoscale substance. The interfacial layer includes the ions, organic and inorganic molecules. The Organic molecules outside layer inorganic nanoparticles are called as surface ligands, capping, stabilizers or passivating agents. A particle has been described as a little object that can act as an entire unit with respect to it's conveyed and elements. These particles are categorized depending on the impact of nano particles

Typically, the unexpected optical properties are possessed by the nanoparticles as they can be little adequate to detain their electrons and generate effects of quantum. In substances composed of nanoparticles, the inclusion of solar radiation can be much higher than it can be in thin films of incessant substance's sheets. The shape, size, and substance of the

### C. High Voltage and XLPE Cables

- A high-voltage (HV) cable is one type of electrical cables that can be utilized for electric power transfer at high level of voltage. This cable contains a conductor and insulator and it can be appropriate for underwater or underground running. The high voltage can take a voltage over 1000 volts. These cables for 3000 and 6000 volts subsist, other than the most of cables have been utilized from 10 kV and rising. These high voltage cables are over 50 kV high voltage cables. For example, the XLPE (Cross-Linked Polyethylene) cable is a one kind of high voltage cables.
- XLPE cables are in the range from 6.6 kV and above that having the semiconducting screens over the every insulated core and conductor. The XLPE cable cannot struggled inexpensively for underground distribution at the voltage level of 11kV with the paper-insulated aluminum- enclosed cable, other than effort can be in the development on regulate and evaluate the design of XLPE cable contains trial fitting, in training for some alter in the condition. The circumstances can be varied for XLPE and it can be the sort in main demand.
- Partial discharge can be acted as localized dielectric breakdown of a little piece of a fluid or solid electrical insulation scheme under the pressure of high voltage, in which space is not linked between the two conductors. The PDs within solid insulation method cannot be observable as a corona discharge can be exposed by a comparatively stable glow or clash discharge in the air.
- The Partial Discharge has also been happened all along the solid insulating substance surface when the surface tangential electric field can be high sufficient to reason a breakdown beside the surface of insulator. These kinds of occurrence marked itself on transparency line insulators, mainly on contaminated insulators in the days of high moisture. Overhead lines can utilize the air as their insulation intermediate.

D. Voltage Gradient

In initial approximation, the main insulation of a high voltage XLPE cable can be regarded as a homogenous cylinder. Its field distribution or voltage gradient is therefore represented by a homogenous radial field. The value of the voltage gradient at a point x within the insulation can therefore be calculated as:

$$E_x = \frac{U_o}{r_x \cdot \ln\left(\frac{r_o}{r_i}\right)} \tag{1}$$


E. Nano Technology techniques

- Cross-linked polyethylene (XLPE) has been created by thermochemical action; the benefit of cross-linking is to inhibit the movement of molecules with respect to each other for enhancing stability at various temperatures compared with the thermoplastic materials. This action permits higher operating temperatures and current rating than polyvinyl chloride. Nanotechnology science gives polymer matrix a reduction in the values of effective permittivity as nanocomposites materials. Nowadays, electric and dielectric properties of power cables insulation materials can be controlled using nanotechnology techniques under various thermal conditions.

$$E_{max} = \frac{2Ud}{r \cdot \ln\left(1 + \frac{4d}{r}\right)} \tag{2}$$

- Electrical trees initiate when there are deterioration caused by partial discharge in gas void or gas crack, or high electric field caused by impurities. It is observed a bush type of tree and branch type tree is observed. The certain length is 20µm. The initiation time, which is the time used for the tree to grow over 20µm in length after it is subject to the electrical stress, have been calculated and analyzed. As the voltage increases, the dispersion of initiation time decreases. This may be because the influences of material microstructure near the needle tip on the initiation of electrical trees are larger when the voltage is lower.


F. Result Analysis



Partial discharge pattern (a)

G. Leakage current waveform

“Magnetization, M”, not just “M”. If including units in the label, present them within parentheses. Do not label axes



Leakage current waveform(a)

H. Conclusion

In this research, the electrical properties have been monitored and modified insulation of enhancing XLPE high voltage cables was improved. A technique of remote sensing of stress and monitoring of partial discharge in High Voltage XLPE cable system has also been discussed. The Monitoring and detection of voltage stress in HV cables was executed I2C protocol by applying the embedded technology. I2C protocol was implemented successfully in this system. Master and slave operations have been controlled by PIC microcontroller. Abnormal voltage stress across the HV cable was corrected by using step up and step down transformer. To implement this proposed method in real-time XLPE cable insulation using some electrical properties. The nano particles SiO2, TiO2 can be added to XLPE cable insulation to the more extension. To examine the improved performance at low computational cost.

REFERENCES

- [1] Ahmed S. G. Khalil, Sonja Hartner, Moazzam Ali, Anoop Gupta, Hartmut Wiggers and Markus Winterer 2010, ‘Stable aqueous dispersions of ZnO nanoparticles for ink-jet printed gas sensors’, pp. 440 – 441.
- [2] Ahmed, N and Srinivas, N 2001, ‘Partial Discharge Severity Assessment in Cable Systems’, in Transmission and Distribution Conference and Exposition, 2001, pp. 849 - 852.
- [3] Ali Kafash Hoshiar, Tuan-Anh Le, Faiz Ul Amin, Myeong Ok Kim and Jungwon Yoon 2017, ‘Functionalized electromagnetic actuation method for aggregated nanoparticles steering’, Annual International Conference of the IEEE Engineering in Medicine and Biology Society (EMBC), pp. 885 – 888.
- [4] Ashish Paramane and Kannaiah Sathish Kumar 2018, ‘Role of Micro and Nanofillers in Electrical Tree Initiation and Propagation in Cross-Linked Polyethylene Composites’, Transactions on Electrical and Electronic Materials’, vol.19, no.4, pp. 254–260.
- [5] Brookhaven National Laboratory 2001, ‘Assessment of Environmental Qualification Practices and Condition Monitoring Techniques for Low-Voltage Electric Cables’, vol. 2, no. 1.
- [6] Caixuan Xu, Anming Hu, Masaki Ichihara, Naomichi Sakai, Izumi Hirabayashi and Mitsuru Izumi 2007, ‘Role of ZrO2/SnO2 Nanoparticles on Superconducting Properties and Microstructure of Melt-Processed Gd123 Superconductors’, IEEE Transactions on Applied Superconductivity, vol.17, no.2, pp. 2980 – 2983.
- [7] Chaikin, S 2001, ‘Partial Discharge Testing – Decreasing the Field Failures of High Voltage Components’, HT LLC, pp. 1-18.
- [8] Du, B. X and Zhu, L. W 2015, ‘Electrical tree characteristics of XLPE under repetitive pulse voltage in low temperature’, IEEE Transactions on Dielectrics and Electrical Insulation, vol.22, no.4, pp. 1801 – 1808.

- [9] Emil Jahoda and Jozef Kudelcik 2017, 'Internal partial discharge in cavity of polyurethane', *Procedia Engineering*, vol.192, pp. 365-369.
- [10] Fengyuan Yang, Gehao Sheng, Yongpeng Xu, Huijuan Hou, Yong Qian and Xiuchen Jiang 2017, 'Partial discharge pattern recognition of XLPE cables at DC voltage based on the compressed sensing theory', *IEEE Transactions on Dielectrics and Electrical Insulation*, vol.24, no.5, pp. 2977 – 2985.
- [11] Granado, J, Torralba, A and Álvarez-Arroyo, C 2016, 'Modeling dispersion of partial discharges due to propagation velocity variation in power cables', *Electric Power Systems Research*, vol.137, pp. 124-132.
- [12] Haddad, A and Warne, D 2004, 'Advances in High Voltage Engineering', London, UK: Institution of Electrical Engineering, London, 2004, ch. 4, pp. 139-185.
- [13] Haghjoo, F, Khanahmadloo, E and Shahrtash, S.M 2012, 'Comprehensive 3-capacitor model for partial discharge in power cables', *COMPEL: The International Journal for Computation and Mathematics in Electrical and Electronic Engineering*, vol. 31, no. 2, pp. 346 - 368.
- [14] Harlin, A, Shuvalov, M, Ovsienko, V and Juhanoja, J 2002, 'Insulation morphology effects on the electrical treeing resistance', *IEEE Transactions on Dielectrics and Electrical Insulation*, vol.9, no.3, pp. 401 – 405.
- [15] Hudon, C and Belec, M 1998, 'The Importance of Phase Resolved Partial Discharge Pattern Recognition for On-Line Generator Monitoring', in *IEEE International Symposium on Electrical Insulation*, Arlington, Virginia, USA, June 1998, pp. 296 - 300.
- [16] IEEE Standards 2001, "IEEE Guide for Field Testing and Evaluation of the Insulation of Shielded Power Cable Systems," *IEEE Power Engineering Society*, New York, NY, Standard 400.
- [17] Isaias Ramirez-Vazquez and Rocio Nava 2013, 'Application of nano particles for the modification of high voltage insulators', *IEEE Transactions on Dielectrics and Electrical Insulation*, vol.20, no.6, pp. 2262 – 2269.
- [18] cables: Conversion of electrical tree to water tree', *IEEE Transactions on Dielectrics and Electrical Insulation*, vol.23, no.3, pp. 1854 – 1861.
- [19] Manoj Yadav, Ravi Shankar R. Velampati, Mandal, D and Rohit Sharma 2017, 'Colloidal nanoparticles based non-volatile memory device: Role of wettability by nanoparticles solvents', *International Conference on Electron Devices and Solid-State Circuits (EDSSC)*, pp. 1 – 2.
- [20] Marek Florkowski, Barbara Florkowska, Andrzej Rybak and Pawel Zydron 2015, 'Metal migration at conductor / XLPE interface subjected to partial discharges at different electrical stresses', *IEEE Transactions on Dielectrics and Electrical Insulation*, vol.22, no.1, pp. 456 – 462.