# Study and Evaluation of Pot holes in Pavement Surface

Ravi Kumar<sup>1</sup>. Mr. Shivam Singh Patel2 <sup>1</sup>PG Student <sup>2</sup>Assistant professor <sup>1,2</sup>Department of CivilEngineering <sup>1,2</sup>,Maharishi University of Information Technology, Lucknow

Abstract— This paper aims at the study of potholes on the bituminous road surface and introducing the antistripping material to the bitumen to increase the durability of the road. Antistripping agents can eliminate the possibility of some instabilities in asphalt, such as crumbling and formation of holes. The idea is to introduce some of anti-stripping agentin the bituminous while contraction of the road to increase the life of the road from potholes and cracking. In this paper, the antistripping material 'bitugrip' is used to improve the adhesionpropertiesofbitumenandaggregates. Thestripping valuedecreaseswhileincreasingthepercentageofbitugripto thebitumen. Anadditionallaboratorystudywasconducted to characterize the performance properties of the antistripping material. Overall, the addition of bitugrip has a positive influence on the adhesion properties between the aggregates and the bitumen and can be used to increase the durability of roads, thereby reduce the maintenance cost of theroads. Key words: Bitumen, Potholes, Bitugrip

## I. INTRODUCTION

In recent years, a lot of research has been done in the area of automated vehicles and automated highway systems. Allthis researchhasacommongoal:tomakedrivingsaferandeasier. It is important to find out solutions to reduce number of accidents. One of the major reason for road accidents is potholes according to the survey conducted by Automobile Association. Vehicles tend to lose balance when they come acrossalargerpothole.Potholesontheroadsareduetomany

reasonslikerains, oilspills, road accidents or inevitable wear and tear make the road difficult to drive upon. Unexpected hurdles on roads may cause more accidents. Also because of the bad road conditions, fuel consumption of the vehicle increases causing wastage of precious fuel. The antistripping material is used to ensure better adhesion between bitumen and the aggregates. Perfect adhesion between the binder and thestoneelements, prevents water from filtering between the two materials, causing premature aging between the bituminous mixture and leading to the formation of the instabilities that decrease the pavement's performance. The deteriorations that characterize road pavements are multiple and each one has well defined cause attributable to the bituminous mixture made and/or to the design and/or the simple end of useful life. One of the main triggers of pavementdeteriorationistheweakeningorthedetachmentof the bitumen film adhering to the surface of the aggregate (stripping).In detail, the factors that affects stripping are-Chemical/physical characteristics of the materials used (bitumen andaggregates);

- Characteristics of the asphalt concrete, with particular reference to the aggregates and the type of mixture produced (dense graded, porous,SMA,etc.)
- Production methodology, hot (HMA), warm (WMA) possible use of water (salts, zeolites, wet sands,etc.)
  Conditionsofuseofthepavementsuchasenvironmental

Ones, the loads, the de-icing method, etc.

- As soon as the bitumen film separates, the pavement immediately starts todeteriorate
- Typical deterioration caused by strippingare-
- Surface crumbling, further intensified if the bitumen content was less thanoptimal,
- Disaggregation and potholeformation,
- Cracking andrutting

II. KEYWORDS OF THE PROPOSEDEXPERIMENT

Here, we are discussing the major keywords used in the experiment.

A. Potholes

Potholes are bowl shaped holes or pits of various sizesfound on pavement surface. These holes usually contain ravelled edges. As water seeps or penetrates through incipient cracks in the surface of pavement during rainy season, it softens the supportinglayers. Theseepedwaterretainedfreezes, expands and pushes up the asphalt layer during winters. The criterion adoptedforthemeasurementofpotholesisdescribed interms of dept.(in mm)and severity levels specified as(ODOT 200;SHRP,1993):The weak portion of the asphalt starts breaking up and raveling under wheel loads during dry season.

- 1) LOW-The hole depth, including delamination of patch, not exceeding 25mm(1").
- MODERATE-The hole depth ranges between 25mm (1") and 50mm(2").
- 3) HIGH-Depth>50mm(2").Thepitextendsbeyondthetop layer of the wearing course but the seldom deeper than 150 or 200mm (CSIR,2010).

The number of potholes at each severity level is recorded up to a maximum of 44 per 161m (0.1 mile) of pavement section. A long pothole or a string of potholes extending over 3.66m (12ft) in length shall be counted as separate potholes (ODOT, 2010).

## B. Bitugrip

It is the product of HINCOAL (Hindustan Colas Private Limited).It prevents bitumen against the stripping action of water. The premature failure of flexible pavement is a widespreadproblem.Theimportantfactorcontributingtothis isimproperadhesionbetweenbitumenandaggregatesmostly due to non-availability of good quality of aggregates and improper drainage system. Hincoal bitugrip is specially designed solution to tackle such problem by enhancing the adhesion of bitumen and ensuring the stability of bituminous pavement. Hincoal bitugrip is very effective while paving roads in high rainfall area and the areas with bad quality of aggregates and improper drainage system. It prevents bitumen against stripping action ofwater.

- C. Advantages of Antistripping Agents
- Enhance the service life of the pavement,
- Excellent adhesion promoter onto all type of aggregates,
- Slow down age hardening ofbitumen,
- Low dosagerequired,
- Stable at high process temperature of hot mix temperature.

## D. Adhesion

The adhesion of bituminous binders involves physical properties of different origin. The adhesion is influenced by thecharacteristicsofboththebitumen(hydrophobicmaterial) and the aggregate used in the mixture (basically hydrophilic material).Other factors are the environmental conditions (humidity and temperature) surface characteristics of the pavement (roughness, porosity and coating) and vehicular movements upon the pavement. Adhesion can be defined generally as the molecular force of attraction between two bodies of different nature in contact with each other. In the contextoftheasphaltconcrete,thecontactisliquid(bitumen) and solid (aggregates). With the mixing between aggregates with bitumen, the latter covers the aggregates. This is to say, theaggregates are made "wet" by the binder. The bituminous bindercreatesasuperficialfilmaroundtheaggregateinorder to obtain a hydrophobic surface, actually impermeable to the particle of water.

## III. EXPERIMENTAL PROGRAM ANDMETHODOLOGY

#### A. Materials and Preparation of AsphaltBinders

Anasphaltbinderof60/70penetrationgradeobtainedpresent investigation. The properties of the supplied material is in liquid.

The HINCOAL Bitugrip has been used to decrease the stripping value. To prepare the sample, 5% by wt. of bitumen is taken and was heated to 160° and blended with bitugrip.Thebitugripwasblendedwiththebitumenbinderat different concentrations (0.5, 1 to 3%) and the stripping test is carried out on the prepared samples to determine the effect of bitugrip on the properties of bitumenbinders.

### B. ExperimentalMethod

Inthisstudy, the hotmelting method has been used for mixing the base bitumen with antistripping agent, bitumen and bitugrip. In hot melting method, the antistripping agent have been introduced to the neatbinder at the elevated temperature

(160° for bitumen)5% by wt. of bitumen has been utilized for all 200gm of aggregates samples, while the bitugrip was variedfrom0.5% to3% by wt.Basedon the bitumen. In every


sample 200gm of clean and dry aggregates passing through 20mm sieve and retained on 12.5mm sieves is taken and the aggregates are heated at 150°C.After that 5% by wt. of bitumen binder was taken and heated at 160°C.The aggregates and the binder are mixed till they are completely coatedandthenthemixtureistransferredintoa500mlbeaker and allow to cool at room temperature for about 2 hours.The distilled water is poured into the beaker to fully immerse the coated aggregates. The beaker is then covered and has been kept in a water bath for about 24 hours at a temperature maintained as 40°C.It should be taken care that the level of water bath is at least half the height of the beaker. After 24 hours the beaker is taken out, and the stripping value istaken out. The bitugrip is added percentage wise to the bitumen as shown in table1.

wt. ofdry	%of	bitugrip	
aggregates	bitumen	used	
(gm)	(%)	(%)	
200	5	0	
200	5	0.5	
200	5	1	
200	5	1.5	
200	5	2	
200	5	2.5	
200	5	3	
	aggregates (gm) 200 200 200 200 200 200 200 200	aggregates      bitumen        (gm)      (%)        200      5        200      5        200      5        200      5        200      5        200      5        200      5        200      5        200      5        200      5        200      5        200      5	

Table 1: percentage of bitumen and bitugrip In every sample and it has been clearly observed that the stripping value decreases on increasing the addition of bitugriptothesample. The stripping value is calculated as the ratio of the uncovered are atothetotal area of the aggregates. The weight of sample is taken as "wt. of dry aggregates + wt. of bitumen+wt. of bitugrip". The addition of 3% of bitugripto the sample shows very less stripping value as shown in Table 2

sample shows very less suppling value as shown in Tablez						
value after	temp.of	stripping				
stripping	waterbath	value				
(gm)	(°C)	(%)				
210	40	92.85				
199.3	40	94.88				
201	40	95.66				
203.5	40	96.83				
205.6	40	97.81				
206	40	97.97				
208.9	40	99.33				
	value after stripping (gm) 210 199.3 201 203.5 205.6 206	value after stripping      temp.of waterbath        (gm)      (°C)        210      40        199.3      40        201      40        203.5      40        205.6      40        206      40				

Table 2: Stripping value



The 1	nercentage	of the	uncovered	area	left as	shown	in	table3
THE	percentage	or the	uncovereu	area	ien as	SHOWI	ш	tables.

Wt. of	Stripping value	Uncovered area
sample(gm)	(%)	(%)
210	92.85	7.15
210.05	94.88	5.12
210.1	95.66	4.34
210.15	96.83	3.17
210.2	97.81	2.19
210.25	97.97	2.03
210.3	99.33	0.67

Table 3: % of uncovered area

The percentage of uncovered area of aggregate decreases on addition of bitu grip.

#### IV. CONCLUSION

Everytimethereisaseparationofthebitumenlayerfromthe stone surface, there is the interposition of water and a direct reduction in performances of the asphalt concrete. Various studies have shown that binder and mixture. Stripping test is carried out to address the effectiveness of bitugrip on the binder properties. Further; an experimental investigation is carried out to characterize the performance of the binder mixed with the bitugrip. Based on the study findings, the following conclusions have beendrawn.

 If it is not possible to alter the nature of the aggregate constituting the bituminous mixtures, the only controllable factor is the bitumen, through the use of antistrippingagents.

- Bitugrip is a chemical mixture containing active functional groups that improves the adhesion of the bitumen film on the surface of theaggregates.
- When it is mixed with the binder it lowers the surface tension of thebitumen.
- As the bitugrip is of low cost, therefore, it is expected to reduce the life cycle cost of the bituminouspavements.
- Using bitugrip increases the durability of the road as proved it thestudy.

#### REFERENCES

- Pavement Evaluation and Maintenance Management System by R Srinivasa Kumar Department of Civil EngineeringUniversityCollegeofEngineering, Osmania University Hyderabad
- [2] Potholes: A Technical Guide To Their Causes, IdentificationAndRepairbyCSIRProjectTeam:DrPhil Paige-Green(project leader)Amrita Maharaj Julius Komba
- [3] ASTUDYOFTHEFUNDAMENTALSOFPOTHOLE FORMATION Eng. Fui Siew1, Toni Ireland-Hay2, GrettaTheobaldStephens2,JohnJ.J.Chen1andMarkP. Taylor3

1Chemical and Materials Engineering Department, The University of Auckland, Private Bag 92019, Auckland, New Zealand

2Comalco Research & Technical Support, P. O. Box 316, Thomastown, Australia

3Light Metals Research Centre, The University of Auckland, Private Bag 92019, Auckland, New Zealand

- [4] POTHOLES AND PITFALLS SPOTTER PRACHI MORE, SUDHISH waterproofing of pavement is the best the best solution. The situation will be in controlled by the use of antistripping agents. The present study focused on understanding the feasibility of adding the bitugrip to the bituminous pavements based on the characteristics of bitumen SURENDRAN, SAYALI MAHAJAN & SAURABH KUMAR DUBEY Department of Computer, Padmabhushan Vasantdada Patil Pratishthan's College of Engineering, Mumbai University, Maharashtra, India
- [5] Pothole Detection and Inter Vehicular Communication Shambhu Hegde, Harish V. Mekali, Golla Varaprasad 2014 IEEE International Conference on Vehicular Electronics and Safety (ICVES) December 16-17,2014. Hyderabad, India
- [6] Repair of Road Distress and Potholes with using Organosilane Based Technologies Dax Patel1, Prof. (Dr.) P. J. Gundaliya2, Dr. Prakash Mehta3 1Finalyear M.E. Student, Civil Engineering Department, L.D.College of Engineering, Ahmedabad, Gujarat, India 2Prof. Civil Engineering Department, L.D.College of Engineering, Ahmedabad, Gujarat, India 3PhD in Civil Engineering Department, Ahmedabad, Gujarat, India
- [7] Potholes Repair Technology- A Review Tanuj Parmar1 Prof. C.B. Mishra2 Dr. Sangita3 Prof. N.F Umrigar4 1ME Student 2Associate Professor 3Sr. Pr. Scientist 4Assistant Professor 1,2,4BVM engineering college, V V nagar, anand, India 3Pavement Engineering Area, CSIR-CRRI, New Delhi,India