

SYNTHESIS, CHARACTERIZATION AND PHOTO-LUMINESCENCE STUDIES OF Gd-Nd RARE EARTH CO-DOPED CALCIUM TUNGSTATE NANO-CRYSTALS

N. Nagaraj

Lecturer in Physics, S.K.R. Government Degree College, Gudur, Nellore Dist.

Email: nnr.lec.phy@gmail.com

ABSTRACT:

We report the synthesis of co-doped Calcium tungstate ($CaWO_4$) nano-crystals with Gadolinium (Gd) and Neodymium (Nd) rare earth ions by hydrothermal synthesis method for the first time. The synthesized nano-crystals were characterized by X-ray diffraction (XRD) with energy dispersive analysis of the X-rays (EDAX) and Field-emission scanning electron microscopy (FESEM), and photo-luminescence excitation studies. The phase of the nano-crystals under study was identified by X-ray diffraction (XRD). The Field-Emission Scanning Electron Microscope (FESEM) image shows that the synthesized nano-crystals are in the size range of 51nm – 80nm. The presence of Gd and Nd rare earth ions in the GD-Nd co-doped $CaWO_4$ nano-crystals was confirmed by the energy dispersive analysis of the X-rays (EDAX). The photoluminescence properties of the Gd-Nd co-doped $CaWO_4$ nano-crystals were compared with the undoped $CaWO_4$ nano-crystals and are reported. The synthesized nano-crystals exhibit emissions at (i) 369nm, 392nm, 435nm and 477nm for an excitation wavelength of 280 nm and (ii) 540nm and 669nm for an excitation wavelength of 490nm. The emission wavelengths clearly indicate the blue light and green light generation, which is significant for developing luminescent materials of tungstate systems.

KEYWORDS: Nano-crystals, X-ray diffraction, Field Emission Scanning Electron Microscopy and Photoluminescence.

1. INTRODUCTION:

The physical parameters such as shape, size and crystallographic structure shows a great impact on the luminescence properties of nanophosphors[1–5]. The morphological changes could lead to a change in the able population of luminescent activators undergoing excitation or emission and are manifested in their quantum yields, luminescence intensities, and lifetimes. Tungstates of Scheelite structure , with the typical AWO_4 formula , have potential applications as scintillators, in catalysis, in optoelectronics, lasers, drug delivery, etc.[6,7].

In their purest state self-activating phosphors, can absorb at a certain wavelength range and then emit at a particular wavelength. For lanthanide-based luminescence, these phosphors are very cost-effective and convenient materials. Calcium tungstate ($CaWO_4$) is a self-activating phosphor which absorbs in the mid-

ultraviolet (mid UV) region at around 250 nm and emits blue light (420 nm). The blue emission of CaWO_4 is due to its tetrahedral WO_4^{2-} group. Its physical and chemical stability, intrinsic blue emission and wide band gap semiconducting nature make it a potential host for luminescence [8–10]. Calcium tungstate (CaWO_4) produce multicolour emissions on being doped with certain lanthanide ions due to the energy transfer from the host to the activator lanthanide ions. By tuning the size, concentration of lanthanide ions or mixing of the dopants there can be a controlled energy transfer from the host to the activator [11–14].

Over the past few decades, several papers were reported on synthesis of single rare earth doped CaWO_4 nano-crystals by hydrothermal process [15–17]. In recent years, codoping of rare earth ions in various hosts using different methods are being carried out to enhance the luminescence properties and improve their applications in biological imaging, white light generation and in optoelectronic devices. The rare earth co-doped system exhibits higher emission intensity than those of the single-doped systems [18–20]. As a part of the synthesis of series of co-doped nano-crystals, in this paper for the first time we report the synthesis of Gd and Nd rare earth ions co-doped CaWO_4 nano-crystals by modified hydrothermal synthesis method using sodium oleate and oleic acid as the capping agents. The synthesized nano-crystals were characterized by X-ray diffraction (XRD) with energy dispersive analysis of the X-rays (EDAX) and Field-emission scanning electron microscopy (FESEM), and photo-luminescence excitation studies.

2. MATERIALS AND METHODS:

2.1. Preparation

The Gd-Nd rare earth co-doped CaWO_4 nano-crystals were synthesized by the following slightly modified hydrothermal process. The chemicals used in this process are of analytical grade and were purchased from Sigma Aldrich. At first a solution was prepared by adding 0.91 g of sodium oleate ($\text{C}_{18}\text{H}_{33}\text{NaO}_2$) to the mixture of 0.25 g ammonium meta tungstate hydrate ($\text{NH}_4\text{H}_2\text{W}_{12}\text{O}_{40}$) and 15 ml double distilled water by stirring for 20 min. Then, another alcoholic solution was prepared by adding 2 ml of oleic acid ($\text{C}_{18}\text{H}_{34}\text{O}_2$) with 8 ml of ethyl alcohol under stirring for half an hour. Now the alcoholic solution so obtained is added to the first prepared solution by stirring for 20 min. Then, the obtained mixture is slowly introduced to a solution formed by 1 mol% $\text{RE}(\text{NO}_3)_3$ ($\text{RE} = \text{Gd}^{3+}$ and Nd^{3+}), 8 ml of double distilled water and 1 gm of $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ and stirred for half an hour. The final obtained solution was transferred into a 50 ml Teflon jar and placed in an autoclave. The autoclave was sealed and maintained at 180 °C for 12 h. The resultant product was centrifuged at room temperature for 15 min at 4500 rpm. The obtained sample was placed in a muffle furnace at 600°C for 5 min, resulting in a white foamy powder.

2.2. Characterization:

To estimate the size of the nano-crystals synthesized and to confirm the incorporation of rare-earth ions into the host lattice (CaWO_4) of nano-crystals different techniques were used. The phase of the formed nano-crystals was identified by X-ray diffraction (XRD) analysis using an automated X-ray powder diffractometer at an operating voltage of 40 kV and current of 30 mA with scanning rate of 4.0 deg min^{-1} , within a range

from 10° to 80° . The size of the nano-crystals formed was determined by using FESEM (Carl Zeiss Model no : Ultra 55). The EDAX (Energy dispersive X ray analysis) was carried out using Oxford: INCAx-act model, device and the incorporation of rare-earth ions was clearly identified. Further, the photoluminescent properties of the Gd-Nd co-doped CaWO_4 nano-crystals were determined at different excitation wavelengths using HORIBA FL3-21 TCSPC model spectrofluorometer.

3. RESULTS AND DISCUSSION:

In this present modified hydrothermal synthesis process oleic acid and sodium oleate act as the capping reagents. The role of oleic acid is to separate out the particles from the super saturated solution and restrict the growth of the CaWO_4 nano-crystals and sodium oleate is used to avoid further nucleation, and acts as a coordinating agent to mediate the nucleation process[17].

3.1. XRD analysis:

The XRD provides information related to the phase of the material. The XRD pattern obtained reveals the crystallinity and phase purity of the Gd and Nd co-doped CaWO_4 nano-crystals, with sharp diffraction peaks as shown in figure 1; All the phases were indexed to scheelite structure.




Figure 1: XRD pattern of the sample, confirming the formation of pure CaWO_4 phase.

3.2. FESEM analysis:

The FESEM (Field-emission scanning electron microscopy) reveals that the average size of the Gd-Nd co-doped CaWO_4 nano-crystals is 65.5nm with relatively uniform size within the range of 51nm-80nm. Figure 2 shows the FESEM images of Gd-Nd co-doped CaWO_4 nano-crystals indicating the high yield of the product obtained using the modified hydrothermal synthesis process. The role of capping agents, sodium oleate and oleic acid is seen significantly in controlling the size of the formed nano-crystals.




Figure 2: FESEM images of Gd-Nd co-doped CaWO₄ nano-crystals

3.3. EDX analysis

The elemental composition of the as-synthesized samples was given by EDX analysis. From Figure 3 the presence of Gd and Nd rare-earth ions in the co-doped nano-crystals is confirmed.




Figure 3: EDAX spectrum of Gd-Nd co-doped CaWO₄ nano-crystals.

3.4. Photo-luminescence studies:

The photoluminescent properties of the Gd-Nd co-doped CaWO₄ nano-crystals were compared with the undoped CaWO₄ nano-crystals and are reported. The PL Spectra of single Nd doped CaWO₄ nano-crystals were studied and the emissions were observed under 587 nm excitation by Suneetha et al. where multiple emission peaks were observed in the range 850-1450 nm using modified Pechini method[21]. The present synthesized co-doped nano-crystals exhibit emissions at (i) 369 nm, 392 nm, 435 nm and 477 nm for an excitation wavelength (λ_{exc}) of 280 nm and (ii) 540 nm and 669 nm for an excitation wavelength (λ_{exc}) of

490nm. The emission wavelengths clearly indicate the blue light and green light generation due to codoping of Gd and Nd rare earth ions in calcium tungstate host lattice. By doping a small amount of Gd^{3+} and Nd^{3+} into CaWO_4 host materials, can improve the emission intensity which may be due to the energy transfer from Gd^{3+} to Nd^{3+} ions and to be confirmed by further spectroscopic techniques.




Figure 4. (a) The Gd-Nd co-doped CaWO_4 NCs - PL spectra ($\lambda_{\text{exc}} = 280\text{nm}$)




Figure 4. (b) The Gd-Nd co-doped CaWO_4 NCs - PL spectra ($\lambda_{\text{exc}} = 490\text{nm}$)

4. CONCLUSIONS:

In summary, the Gd-Nd co-doped CaWO_4 nano-crystals were synthesized successfully by the hydrothermal synthesis route using oleic acid and sodium oleate act as the capping reagents, for the first time and further a

series of lanthanides were chosen for future scope of work. The average size of the nano-crystals synthesized using this method is within 51nm-80nm range as observed by FESEM. The presence of Gd^{3+} and Nd^{3+} rare earth ions in Gd-Nd: CaWO₄ nano-crystals is confirmed by EDAX. PL studies were used to further confirm the presence of Gd and Nd ions and shows the emission wavelengths within the range of 369 nm to 670nm at excitation wavelengths 280nm and 490nm respectively. The emission wavelengths clearly indicate the blue light and green light generation. This work shows that, by doping a small amount of Gd^{3+} and Nd^{3+} into CaWO₄ host materials, can improve the emission intensity [22] and the multiple luminescence emission can be realized which is significant for developing luminescent materials of tungstate systems. This may be due to the energy transfer from Gd^{3+} to Nd^{3+} ions or vice-versa and needs to be confirmed by further spectroscopic techniques. The results clearly indicate that the nano-crystals under study can be used for the white light generation applications with suitable modifications.

References:

1. Brenier, G. Jia and C. Tu, *J. Phys.: Condens. Matter*, 2004; **16**:9103–9108.
2. Y. Hu, W. Zhuang, H. Ye, D. Wang, S. Zhang and X. Huang, *J. Alloys Compd.*, 2005; **390**:226–229.
3. J. Ninkovic', G. Angloher, C. Bucci, C. Cozzini, T. Frank, D. Hauff, H. Kraus, B. Majorovits, V. Mikhailik, F. Petricca, F. Probst, Y. Ramachers, W. Rau, W. Seidel and S. Uchaikin, *Nucl. Instrum. Methods Phys. Res., Sect. A*, 2005; **537**: 339–343.
4. Z. Shan, Y. Wang, H. Ding and F. Huang, *J. Mol. Catal. A: Chem.*, 2009; **302**:54–58.
5. X. Zhai, M. Yu, Z. Cheng, Z. Hou, P. Ma, D. Yang, X. Kang, Y. Dai, D. Wang and J. Lin, *Dalton Trans.*, 2011; **40**:12818–12825.
6. T. J. Boyle, P. Yang, K. Hattar, B. A. Hernandez-Sanchez, M. L. Neville and S. Hoppe, *Chem. Mater.*, 2014; **26**: 965–975.
7. M. J. Treadaway and R. C. Powell, *J. Chem. Phys.*, 1974; **61**: 4003–4011.
8. Y. Xu, Y. Wang, L. Shi, L. Xing and X. Tan, *Opt. Laser Technol.*, 2013; **54**:50–52.
9. G. S. Ningombam and R. S. Nongmaithem, *Int. Nano Lett.*, 2017; **7**:133–140.
10. G. S. Ningombam, N. R. Singh and R. S. Ningthoujam, *Colloids Surf., A*, 2017; **518**, 249–262.
11. C. Burda, X. Chen, R. Narayanan, and M. A. El-Sayed, *Chem. Rev.*, 2005; **105**: 1025–1102.
12. H. G. Yang, C. H. Sun, S. Z. Qiao, J. Zou, G. Liu, S. C. Smith, H. M. Cheng, and G. Q. Lu, *Nature*, 2008, 453, 638.
13. V. M. Longo, L. Gracia, D. G. Stroppa, L. S. Cavalcante, M. Orlandi, A. J. Ramirez, E. R. Leite, J. Andre's, A. Beltra'n, J. A. Varela and E. Longo, *J. Phys. Chem. C*, 2011; **115**:20113–20119.
14. Lingna Suna,b, Minhua Caoc, Yonghui Wangc, Genban Suna, b, Changwen Hua *Journal of Crystal Growth* **289** (2006) : 231–235.
15. P. Suneetha, Ch. Rajesh and M. V. Ramana *Mater. Res. Express* **4** (2017): 045013
16. Wang W, Yang P, Gai S, Niu N, He F and Lin J 2010 *J. Nanopart. Res.* **12** 2295

17. Qi Fan, Xiaoxia Cui, Haitao Guo, Yantao Xu, Guangwei Zhang and Bo Peng, *Journal of Biomaterials Applications* 0(0): 1–27.
18. P Suneetha, Ch Rajesh and M V Ramana, *Mater. Res. Express* 4 (2017): 085020
19. Guiqiang Chen, Fengli Wang, Wenchao Ji, Yanxia Liu, Xiao Zhang, *Superlattices and Microstructures* 90 (2016): 30-37.
20. N. Thejokalyani, S.J. Dhoble, *Renew. Sustain. Energy Rev.* 32 (2014): 448–467.

