

A Review on Impact of Waste Rubber Tyres on Subgrade of Srinagar Banihal-Highway

Aneesul Islam¹, Nasir Ali²

¹M.Tech scholar, Civil Department, ²Assistant Professor, Civil Engineering Department, Galaxy Global Group of Institution, Dinarapur (Ambala)

ABSTRACT

Automotive uses are increasing every day as a result of which the loss of tyres is increasing. The waste tyres, in India, are graded as solid waste. The proper handling of these waste tyres has become difficult due to the production of tyres with synthetic rubber. It is estimated to dispose of 60 to 70 per cent of waste tyres in different areas in an inappropriate manner. As a result, eco-systems such as air pollution and aesthetic pollution are experiencing considerable harm. To avoid this damage, we can utilize these tyre wastes with technical development in different fields like using tyre wastes in construction of flexible pavements. It is not only to decrease the pollution but also to decrease the use of aggregates which is in low quantity. In this investigation, I will put my effort to make an effective use of waste tyres in the subgrade of Srinagar-Banihal highway pavement.

Keywords: Pavement, Subgrade, CBR, Modified Proctor test, Waste Rubber tyres.

1. INTRODUCTION

Since time immemorial, civil engineering has been very kind to humanity, and is one of the ancient sciences. What Civil Engineering has not given us, from underground metro to sky-high towers, from clean, pure water to drink, from airways to highways, to a non-reluctant and welcoming atmosphere. The list of deeds never shortens, it goes on. The fact that an earthling is not a good civil engineer until and unless he or she is not a good environmentalist is well-versed. And we had made an effort to make our atmosphere less hostile and non-obnoxious, to maintain and retain this environmental dimension of Civil Engineering. What drives and makes Civil Engineering conform? Civil Engineering is this law and tradition to search and quest for more than better without in the future making the resources less or more redundant. As a civil engineer I mainly focused on the same idea and stuck to the history and culture and essence of civil engineering. In this paper I have provided a series of engineering results regarding the **IMPACT OF WASTE RUBBER TYRES ON SUBGRADE OF SRINAGAR-BANIHAL HIGHWAY**, which I am very sure, will provide the edge to the scholars in future.

Followed by the US, India has the second-largest road network in the world. The bigger the road network, the bigger the car density of India will be. As a geotechnical engineer, my aim is to meet and develop road components not only from the point of view of engineering but also from the point of view of road users. With the advancement of technology and the sophisticated life style of the masses, the use of automobiles is increasing day by day. As the number of vehicles grows so are the heaps of discarded rubber tyres, or the waste of tyres. Today most tyres, particularly those fitted to motor vehicles, are made from synthetic rubber. Waste tyres, in India, are classified as solid waste. The proper disposal of these waste tyres has become difficult due to the manufacture of tyres with synthetic rubber. It is estimated that 60 to 70 per cent of waste tyres are inappropriately disposed of in various areas. As a result of this, there is a great damage to eco-system like air pollution and aesthetic pollution. As discussed, earlier environment is our duty and to prevent this harm by inadequate disposal of worn-out tyres, we can use these tyre-wastes with technological advancement in different fields, such as using tyre-waste in flexible pavements construction.

It is not only about reducing pollution but also about reducing the quantity of materials required in flexible pavements. In this investigation, I put my efforts to make an effective use of waste tyres to stabilise the subgrade of highway pavement. Generations of scrap tyres, everywhere in the world, are always on the growing trend. Most of them end up in the already congested landfill, or become breeding grounds for mosquitos. Worst when they are burned. Our goal is to research the suitability of shredded rubber tyres for their application in pavement engineering. As previously reported, one of the key problems relating to the management of scrap tyres was their proper disposal. So, in this project work, an effort has been made to make use of these waste tyres in subgrade of the flexible pavement. Usually tyres are used in civil engineering applications in a shred form referred to as "tyre chips" or "tyre threads" These chips are between 12 and 50

mm in size or threads passing through 4.75 mm IS Sieve and with steel belt removed during processing. Approximately 12 million scrap tyres were used for civil engineering applications in 1995 and 15 million in 1996, including leachate collection systems, landfill cover, artificial reefs, and clean fill for road embankments, road bed support and similar projects (Liu et al., 2000). Although of their particular characteristics the use of tyre shreds for civil engineering applications has many advantages. One of the most significant properties is that shreds of tyres are a lightweight material. Compared to other light-fill materials it is relatively inexpensive. Tyre shreds cause low horizontal stresses because they are lightweight and have relatively high shear power. However, tyre shreds have not been tried extensively for using it in subgrade and subbase layers of the pavement. An attempt has been made in this project to discover its possible use in those layers.

Now, talking about Srinagar-Banihal highway which is the only connecting link to the subcontinent and is still under construction for almost 20 years now. There are many low-lying areas like Awantipora stretch or Panthachowk- Nowgam area where the construction of highway is still going on. Also, worthy to mention there is no such area for deposition of solid wastes like tyre waste. What we do there is simply dispose the wastes on the banks of Jhelum which not only pollutes the water body but affects the surrounding environment drastically.

Objectives:

I aimed to know how the parameters of the soil subgrade will affect by the introduction of waste rubber which later was executed in a very positive fashion and the results were quite satisfactory.

2) LITRATURE REVIEW

1. **Tatlisoz, Benson, Edil, (1997)** decrypted soil-tyre chip mixtures are unique fill materials with high compressibility and ductility. Soil-tyre chip mixtures also have unique mechanical properties that are primarily governed by the tyre chip content, not by soil type.
2. **Zornberg, Costa, Vollenweider, (2000)** conducted a field investigation to assess the mechanical behaviour of an experimental embankment fill built with tyre shreds and cohesive soil. Immediately after construction, the embankment was submitted to heavy truck traffic and settlements were monitored for over two years. The results indicate that the embankment sections built with tyre shreds and cohesive soil showed satisfactory long term performances during traffic exposure.
3. **Tatlisoz, Edil, Benson, (2001)** assessed the shear strength and geosynthetic interaction of tyre chip and soil-tyre chip backfills that may be used for geosynthetic reinforced walls and embankments and concluded that Soil-tyre chip mixtures have significantly higher shear strength than the soil used in the mixture.
4. **Hassana, Hassan, Marei, Hashem, (2005)** based on their tests involving triaxial test and CBR test on shred tyre reinforced soil, concluded that the presence of shredded waste tyres in sand improves the stress-strain properties for all different sizes and contents of shreds waste tyre over that pure sand. The maximum deviator stress of randomly reinforced sand occurs at a higher axial strain compared to sand alone. CBR values increases with the increase of shreds tyre content up to 3 % content. After this content the increasing of CBR value decreases with the increase of shreds tyre content in both soaked and unsoaked specimens.
5. **Prasad, Prasad Raju, Ramana Murthy, (2008)** carried out CBR and direct shear tests for finding the optimum percentages of waste plastics and waste tyre rubber in gravel subbase material. Based on these results, laboratory model pavement studies were conducted with optimum percentage of waste plastics and waste tyre rubber in gravel subbase, laid on expansive soil subgrade in the flexible pavement system. The load carrying capacity of the model flexible pavement system significantly increased when the gravel subbase was reinforced with waste plastics as well as waste tyre rubber when compared to unreinforced subbase.
6. **Boscher and Edil (1992, 1994)** studied on soil-tyre chip mixtures and indicated improved frictional characteristics, increased resistance to dynamic loading and improved drainage characteristics of the soil. The tyre chips having size less than 20 mm have been used.
7. **Mc. Donald (1996)** developed rubber-bitumen compositions containing up to 25% cryogenically recovered rubber tyre. It has been reported that at high temperatures, jelly like material with improved elastic properties is produced. The blends were recommended for prevention of reflection cracking in bituminous pavements.
8. **Alocke and Gregg, Oliver, Jain and Shukla Nagarajan and Thirunavakkarasu, (1992)** made attempts to investigate the effect of Rubber Additive in Bituminous Paving Mixture and it is reported that partial replacement of rubber can be made in bitumen without much affecting the properties of bitumen. The rubber from discarded tyres received greater attention due to comparative cost and prevention of air pollution from environmental point of view.

9.S.Yoon et al. (2006) reported the performance of a test embankment constructed of Sand-Tyre shred mixture as fill

material. The embankment was observed to perform satisfactorily exhibiting a maximum settlement of 12 mm.

3)CONCLUSION

The following findings are drawn from the experimental investigations and the results obtained:

- 1.1 Waste tyre combined with soil has shown an increase in CBR value and a steady decrease in MDD.
- 1.2 Giving importance to the CBR value in pavement design, the mixing of waste tyres in the soil is found to be successful when the waste rubber is combined with the soil up to 5 per cent by weight.
- 1.3 Soil-reinforced waste tyre showed an improvement in the CBR value with an addition of up to 5% and subsequently decreased with an additional increase in soaked tyre content.
- 1.4 The drop in MDD can be due to the loose grip of the rubber surface with the soil and the weight of the waste rubber unit is lower than that of the soil.
- 1.5 In this particular soil, the waste tyre can be used effectively in subgrades to improve its CBR value in areas where the rainfall is lower and the groundwater table is at a great depth below.
- 1.6 The decrease of the OMC to 5% of the waste tyre mixed sample is due to the good water absorption characteristic of the waste tyre, and thereafter, with 7% and 10% of the waste tyre mixture in the soil sample, the increase in the OMC credits is due to the uneven compaction that leaves significant amounts of waste in the sample..
- 1.7 The waste tyre mix is up to 5% to the degree that it is feasible in the pavement sub-layer because it will effectively minimize the amount of soil and substantially reduce the environmental aesthetic emissions.
- 1.8 An increase in CBR value of 2% can significantly reduce the total thickness of the pavement and hence the total cost involved in the project.

It is therefore concluded that waste rubber (up to 5 per cent) can be used to enhance the soil's geotechnical properties. By using waste crumb rubber immensely to enhance the geotechnical properties of clay, it helps to address the safety and environmental problems associated with disposal of this hazardous waste

4) REFERENCES

1. Khanna, S.K. and Justo, C.E.G 2002 'HighwayEngineering'.
2. Ghatge Sandeep Hambirao., and Rakaraddi, P.G. (2014) "Soil Stabilization Using Waste Shredded Rubber Tyre Chips". Journal of Mechanical and Civil Engineering (JMCE), Vol.11
3. Bosscher, P. J., Edil, T. B. and Eldin, N.(1993)
4. Construction and performance of shredded waste tyre test embankment, Transportation Research Record No. 1345, *Transportation Research Board*, Washington,D.C.
5. Foose, G.J, Benson, C.H., and Bosscher, P.J.(1996)
6. 'Sand reinforced with shredded waste tyres', *Journal of Geotechnical Engineering*, Vol. 122, No.9
7. V. Vinot, B. Singh, Investigation on Behaviour of Soils Reinforced With Shredded Waste Tyres, In: Proceedings of the Indian Geotechnical Conference Igc, Geotide. Guntur, INDIA,2009.
8. R.M. Subramanian, S.P. Jeyapriya, Study on Effect of Waste Tyres in Flexible Pavement System, Indian Geotech Soc. Chennai Chapter,2009
9. IS: 2720 Methods of test for soil: Grain size analysis, Bureau of Indian Standards, NewDelhi.
10. 5. IS: 2720 Methods of test for soil: Determination of liquid limit and plastic limit, Bureau of Indian Standards, NewDelhi.
11. IS: 2720 Methods of tests for soil : Determination of water content- dry density relation using light compaction, Bureau of Indian Standards, NewDelhi.
12. Rao G.V and Dutta R.K (2001), "Utilization of shredded tyres in highway engineering", Proceedings of the International seminar on sustainable development in road transport, NewDelhi
13. MORTH-2001: Specifications for Roads and Bridgeworks, Ministry of Road Transportation and Highways, Govt. ofIndia.