JETIR.ORG ISSN: 2349-5162 | ESTD Year : 2014 | Monthly Issue
JOURNAL OF EMERGING TECHNOLOGIES AND INNOVATIVE RESEARCH (JETIR)
An International Scholarly Open Access, Peer-reviewed, Refereed Journal

Review on journal bearing wear and lubrication methods

Sagar Bharat Male[1], Kishor Mahajan[2], Tushar Koli[3]

[1]PG student, Mechanical Engineering Dept. GF's Godavari College of Engineering Jalgaon, Maharashtra
[2]Assistant Professor, Mechanical Engineering Dept, GF's Godavari College of Engineering Jalgaon, Maharashtra
[3]Assistant Professor, Mechanical Engineering Dept, GF's Godavari College of Engineering Jalgaon, Maharashtra

Abstract:

Journal bearings are critical components in rotating machinery, providing smooth motion and reducing friction between moving parts. Over time, however, these bearings are subjected to wear, which can lead to performance degradation, increased maintenance costs, and even catastrophic failures. This review article provides a comprehensive analysis of the mechanisms of wear in journal bearings, including adhesive, abrasive, corrosive, and fatigue wear. It also explores the factors that influence wear rates, such as lubrication conditions, material properties, load, speed, and operating environment. The article highlights recent advances in wear-resistant materials and surface coatings, as well as emerging diagnostic techniques for monitoring wear in real-time. By synthesizing findings from recent studies, this review aims to offer insights into optimizing journal bearing design and maintenance strategies to enhance reliability and extend service life in various industrial applications. Future research directions are also discussed, emphasizing the need for more sustainable and efficient approaches to mitigate wear in journal bearings.

Introduction

Journal bearings are widely used in various industrial applications, such as turbines, compressors, pumps, and engines, due to their ability to support high loads and accommodate moderate speeds. Despite their importance, journal bearings are susceptible to wear over time, leading to degradation in performance and potential failure of machinery. Understanding the wear mechanisms and factors influencing wear is essential for improving bearing life and optimizing maintenance strategies.

Types of Wear in Journal Bearings

Adhesive Wear:

Occurs when two contacting surfaces adhere to each other and material transfers from one surface to the other.

Common in situations where lubrication is insufficient, leading to metal-to-metal contact.

Abrasive Wear:

Caused by hard particles or asperities between the bearing surfaces, leading to material removal.

Often results from contamination in the lubricant or the presence of hard particles in the bearing material itself.

Fatigue Wear:

Results from repeated cyclic loading, causing cracks and material spalling over time.

Common in high-load applications where the bearing is subjected to continuous stress.

Corrosive Wear:

Occurs when chemical reactions between the bearing material and the environment lead to material degradation.

Often exacerbated by the presence of moisture, acidic environments, or corrosive lubricants.

Erosive Wear:Caused by the impact of solid particles or fluid jets on the bearing surface, leading to material removal.

Common in environments where high-speed particles or fluids are present.

Factors Influencing Wear in Journal Bearings

Lubrication:

Adequate lubrication is crucial in preventing metal-to-metal contact and reducing friction.

Poor lubrication can lead to increased wear rates, while excessive lubrication may cause issues such as hydrodynamic instability.

Load and Speed:

Higher loads and speeds can increase wear rates due to the increased stress and friction on the bearing surfaces.

However, too low a load can also cause issues, such as insufficient film thickness, leading to increased wear.

Material Properties:

The hardness, toughness, and compatibility of the bearing and shaft materials play a significant role in determining wear resistance.

Advanced materials, such as composite materials and coatings, are often used to enhance wear resistance.

Contamination:

The presence of foreign particles in the lubricant or bearing surfaces can lead to abrasive and erosive wear.

Proper filtration and sealing can help minimize contamination and reduce wear.

Temperature:

Elevated temperatures can accelerate wear by reducing lubricant viscosity and increasing oxidation rates.

Thermal management strategies, such as cooling systems and the use of high-temperature lubricants, are essential in high-temperature applications.

Effects of Wear on Journal Bearings

Wear in journal bearings can lead to several detrimental effects, including:

Increased Friction:

As wear progresses, the friction between the bearing and shaft surfaces increases, leading to higher energy consumption and potential overheating.

Loss of Dimensional Accuracy:

Wear can cause changes in the bearing's dimensions, leading to misalignment and vibration issues.

Decreased Load-Carrying Capacity:

Worn bearings may not be able to support the same load as new bearings, potentially leading to bearing failure.

Reduced Operational Efficiency:

Increased friction and misalignment can reduce the overall efficiency of the machinery, leading to higher operational costs.

Potential for Catastrophic Failure:

In severe cases, wear can lead to bearing seizure or complete failure, resulting in costly downtime and repairs.

Mitigation Strategies for Journal Bearing Wear

Improved Lubrication Systems:

Ensuring proper lubrication through automated systems, high-quality lubricants, and regular maintenance can significantly reduce wear.

Material Selection:

Using wear-resistant materials, such as ceramics, composites, or coated metals, can enhance the durability of journal bearings.

Contamination Control:

Implementing effective filtration systems and sealing techniques can help prevent the ingress of contaminants that cause wear.

Condition Monitoring:

Regular monitoring of bearing conditions, such as temperature, vibration, and oil analysis, can help detect early signs of wear and allow for timely intervention.

Optimized Design:

Designing bearings with appropriate clearances, surface finishes, and load capacities can reduce wear and extend bearing life.

Lubrication

Effective lubrication plays a crucial role in reducing journal bearing wear by minimizing friction and preventing direct metal-to-metal contact between the bearing surface and the shaft. Here are key strategies for using lubrication effectively to reduce wear in journal bearings:

1. Selecting the Right Lubricant:

- Viscosity: Choose a lubricant with the appropriate viscosity for the operating conditions (load, speed, temperature). Higher viscosity oils provide better film thickness, reducing metal-to-metal contact, while lower

viscosity oils are preferred for high-speed applications where low friction is critical.

- Additives: Use lubricants with anti-wear additives, such as zinc dialkyldithiophosphates (ZDDP), which form protective layers on metal surfaces to reduce wear. Other additives, like extreme pressure (EP) additives, help protect bearings under high loads.
- Base Oil Selection: Synthetic oils generally offer better thermal stability, oxidation resistance, and performance at extreme temperatures compared to mineral oils, making them suitable for demanding applications.

2. Ensuring Adequate Lubrication Supply:

- Hydrodynamic Lubrication: Ensure that the journal bearing operates under full hydrodynamic lubrication, where a continuous film of lubricant separates the shaft and bearing surfaces. This can be achieved by maintaining proper oil supply pressure and flow rates.
- Boundary Lubrication: In cases where full film lubrication is not possible, boundary lubricants or solid lubricants (such as graphite or molybdenum disulfide) can reduce wear by forming a protective layer on the bearing surfaces.
- Oil Circulation Systems: Implementing oil circulation systems that continuously supply fresh lubricant can help maintain optimal lubrication conditions, especially in high-temperature or contaminated environments.

3. Monitoring and Maintaining Lubricant Condition:

- Oil Analysis: Regular oil analysis can help detect lubricant degradation, contamination, and the presence of wear particles. This allows for timely interventions, such as oil changes or filtration, to maintain lubrication effectiveness.
- Temperature Control: Excessive temperatures can cause oil breakdown and reduce its lubricating properties. Implement cooling systems or choose lubricants with high thermal stability to prevent overheating.

4. Minimizing Contaminants:

- Filtration: Use high-efficiency filters to remove contaminants such as dirt, metal particles, and water from the lubricant. Contaminants can accelerate abrasive wear and degrade the lubricant.
- Sealing Systems: Proper sealing of the bearing housing helps prevent ingress of contaminants and ensures the lubricant remains clean.

5. Design Considerations:

- Surface Roughness: Ensure that the bearing and shaft surfaces are smooth and well-finished to promote the formation of a stable lubricant film.
- Alignment and Load Distribution: Proper alignment and load distribution reduce localized stress and wear, ensuring even lubricant film formation across the bearing surface.

6. Use of Advanced Lubrication Techniques:

- Nanoparticle Lubricants: Research into lubricants containing nanoparticles shows promise in reducing wear. These nanoparticles can enhance the formation of protective films or act as rolling elements to reduce friction.
- Smart Lubrication Systems: Real-time monitoring and automated lubrication systems can adjust the lubricant supply based on operating conditions, ensuring optimal lubrication at all times.

Conclusion

Journal bearing wear is a critical concern in rotating machinery, impacting performance, efficiency, and reliability. By understanding the various wear mechanisms and factors influencing wear, engineers can implement effective mitigation strategies to extend the life of journal bearings and prevent costly failures. Ongoing research in materials science, lubrication technology, and condition monitoring will continue to play a key role in advancing the durability and performance of journal bearings in industrial applications.

Effective lubrication is key to reducing journal bearing wear. By selecting the right lubricant, ensuring adequate supply, maintaining lubricant quality, minimizing contaminants, and incorporating advanced lubrication technologies, the wear on journal bearings can be significantly reduced, leading to improved reliability, reduced maintenance, and longer bearing life.

References

[1] Shyam Bahadur et al (2000) The development of transfer layers and their role in polymer tribology.
[2] Dumbre Omkar, Khillari Shubham(2016) A REVIEW PAPER ON STUDY OF WEAR ANALYSIS OF BEARING MATERIAL.
[3] Erol Feyzullahog˘lu , Nehir Sakirog˘lu(2009) The wear of aluminium-based journal bearing materials under lubrication.
[4] Gengyuan Gao, Zhongwei Yin, Dan Jiang, Xiuli Zhang; Numerical analysis of plain journal bearing under hydrodynamic lubrication by water; Tribology International, Volume 75, Pages 31-38, July 2014
[5] Emiliano Mucchi, Alessandro Agazzi, Gianluca D'Elia, Giorgio Dalpiaz; On the wear and lubrication regime in variable

displacement vane pumps; Wear, Volume 306, Issues 1–2, Pages 36-46, 30 August 2013.

[6] E.N. Santos, C.J.C. Blanco, E.N. Macêdo, C.E.A. Maneschy, J.N.N. Quaresma; Integral transform solutions for the analysis of hydrodynamic lubrication of journal bearings; Tribology International, Volume 52, Pages 161- 169, August 2012.

[7] Peng Liang, Changhou Lu, Jie Ding, Shujiang Chen; A method for measuring the hydrodynamic effect on the bearing land; Tribology International, Volume 67, Pages 146-153, November 2013.

[8] N.B. Naduvinamani, A. Siddangouda; "Effect of surface roughness on the hydrodynamic lubrication of porous stepslider bearings with couple stress fluids"; Tribol.

[9] J. D. Bressana, D. P. Darosa, A. Sokolowskib, R. A. Mesquitac, C. A. Barbosad, Influence of hardness on the wear resistance of 17-4 PH stainless steel evaluated by the pin-on-disc testing, journal of material processing technology, Vol. 2, pp 353-359, 2008.

[10] Priyanka Tiwari and Veerendra Kumar, Analysis of Hydrodynamic Journal Bearing: A Review, International Journal of Engineering Research & Technology (IJERT) Vol. 1, Issue 7, ISSN: 2278-018 September 2012.